

DATA SHEET - TECHNISCHES DATENBLATT - FICHE TECHNIQUE

2065 AS

Polyester Base TPU With Antistatic

Attribute	Test Method	Units	Test Result
Finished Weight	ASTM D751	g/m <sup>2</sup>	1150 g/m <sup>2</sup> (+/- 50)
Thickness		mm	1.0 (+/- 0,1)
Breaking Strength	ASTM D751 B	N/50mm	>2300/1800
Tear Strength	ASTM D751	N	>200
Seam Strength (Matt) (1/8" RF breakaway)	ASTM D751	N/50mm	>600/500
Seam Strength (Bright) (1/8" RF breakaway)	ASTM D751	N/50mm	>500/400
Elect. Feature	Static , surface resistant	Ohm	10 <sup>8</sup> ~10 <sup>9</sup>

Technical data shown above are average values from the current production.

Die angegebenen technischen Daten sind Durchschnittswerte der Produktion, die lediglich die technischen Eigenschaften und die chemische Zusammensetzung der gelieferten Ware beschreiben.

Sie sind keine zugesicherten Eigenschaften im Sinne des BGB.

Les données techniques ci-dessus sont des valeurs moyennes de la production courante.